



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B01J 31/02, 31/14</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 95/24268</b> <b>(43) International Publication Date:</b> 14 September 1995 (14.09.95)
<b>(21) International Application Number:</b> PCT/US95/02603 <b>(22) International Filing Date:</b> 3 March 1995 (03.03.95) <b>(30) Priority Data:</b> 08/209,669 10 March 1994 (10.03.94) US <b>(71) Applicant:</b> NORTHWESTERN UNIVERSITY [US/US]; 633 Clark Street, Evanston, IL 60208 (US). <b>(72) Inventors:</b> MARKS, Tobin, J.; 2300 Central Park Avenue, Evanston, IL 60201 (US). JA, Li; Apartment 313, 7120 North Sheridan Road, Chicago, IL 60626 (US). YANG, Xinmin; Apartment 703, 800 Hinman Avenue, Evanston, IL 60202 (US). <b>(74) Agent:</b> FENNELLY, Richard, P.; Akzo Nobel Inc., 7 Livingstone Avenue, Dobbs Ferry, NY 10522 (US).		<b>(81) Designated States:</b> CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METALLOCENE CATALYST CONTAINING BULKY ORGANIC GROUP		
<b>(57) Abstract</b>		
<p>An ionic metallocene catalyst for olefin polymerisation which comprises: (1) a cyclopentadienyl-type ligand, a Group IVB transition metal, and alkyl, aryl, or hydride substituents, as a cation, and (2) a weakly coordinating anion comprising boron substituted with halogenated, such as tetra fluoro, aryl substituents preferably containing silylalkyl substitution, such as para-silyl t-butylidimethyl.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

METALLOCENE CATALYST CONTAINING BULKY ORGANIC GROUP

This invention was made with Government support under Contract No. 86ER 13511 awarded by the Department of Energy. The Government has certain rights in this invention.

BACKGROUND OF THE INVENTION

Metallocene cationic salts of the general type  $Cp_2MR^+X^-$  (Cp being a cyclopentadienyl-type ligand; M being a Group IVB metal such as titanium, zirconium, or hafnium, R being alkyl, aryl or hydride; and X being a weakly coordinating anion form the basis for a large family of active, efficient and selective olefin polymerization catalysts. The performance of these systems is exceedingly sensitive to the nature of X with X being, preferably,  $RMAO^-$  (MAO being methylaluminoxane),  $RB(C_6F_5)_3^-$ , and  $B(C_6F_5)_4^-$ . While  $B(C_6F_5)_4^-$  appears to give the most active catalysts, such catalysts suffer from insolubility and thermal instability.

U.S. Patent No. 5,153,157 to G. G. Hlatky et al. discloses catalyst systems in which the anion is said to be bulky, labile and non-coordinateable with the Group IV metallocene containing component. Despite a rather generalized disclosure of possible substitution possibilities on the aromatic hydrocarbon groups of the anion, this patent only exemplifies the use of tetraphenyl borate and tetrapentafluorophenyl borate species without any suggestion that the presence of certain types of substitution on these structures would yield systems having enhanced solubility and thermal stability characteristics. There is, furthermore, no enabling description as to how such enhanced systems might be made.

- 2 -

DESCRIPTION OF THE INVENTION

The present invention relates to a modification of the aforementioned type of catalyst systems by providing a weakly coordinating anion comprising boron substituted with halogenated aryl substituents containing silylalkyl substitution. The presence of silylalkyl substitution on the aryl moiety, preferably in the para-position increases the solubility and thermal stability of the resulting metallocene salts.


It is within the contemplation of the present invention that a variety of general boron-containing structures can be employed in accordance with the present invention. For example, boron tetraaryl structures in which the four aryl groups are phenyl containing four fluorine substituents and a bulky "R" group in the ortho, meta or para-position to increase the solubility and thermal stability of the catalyst system are contemplated herein. Representative R groups include C<sub>1</sub> to C<sub>20</sub> alkyl or C<sub>1</sub> to C<sub>20</sub> alkyl-substituted group 14 metalloids (e.g., silicon, germanium, or tin). Also contemplated are analogous boron species where the aryl moiety can comprise a biphenylene structure in which the phenyl ring closest to the boron atom contains four fluorine substituents with the more remote phenyl ring containing four fluorine substituents and the type of R group defined above. If desired, the biphenylene configuration of the aryl substituents can be reconfigured to a naphthyl configuration with the same type of R group being used to improve the solubility and thermal stability of the catalyst that results as compared to one not containing the bulky R substituent.

The silylalkyl substitution, which represents a preferred embodiment herein, is of the structure



- 3 -

with R<sup>1</sup> being the same or different and being selected from straight and branched alkyl, preferably lower alkyl of from one to four carbon atoms. Representative alkyl groups include methyl, ethyl and t-butyl. A particularly preferred silyl substituent comprises one t-butyl and two methyl groups in aryl substituents also containing four fluorine atoms. The thermal stability for such a system is significant since it has been found stable with no significant thermal decomposition to 100°C over a period of hours. In contrast, the known system



Cp'' being 1,2-dimethylcyclopentadienyl) is only stable below 0°C for significant periods of time.

The general type of procedure for making the desired metallocene catalyst of the present invention can be practiced by using the general type of procedure disclosed in Examples 1-4, below, which depict the synthesis of a particularly preferred embodiment of the invention.

Initially, a precursor for the anion can be formed, for example, by reaction of a halogenated benzene analog of the ultimately desired, non-silyl substituted structure, a suitable metallating agent, such as an alkyl lithium reagent, and a silylalkyl trifluoromethane sulfonate. The resulting reaction forms the desired silylalkyl-substituted halogenated benzene precursor for the subsequent step in which such a precursor is reacted with a suitable metallating agent, such as an alkyllithium reagent, and boron trihalide to form a lithium and borate-containing salt species which is in turn reacted with triphenylmethyl chloride to form the triphenyl carbenium precursor. This resulting precursor can be reacted with a selected bis(cyclopentadienyl) zirconocene reagent to form the ultimately desired catalyst salt.

If desired, the catalyst salt can be generated in-situ by mixing the desired metallocene (e.g., Cp<sub>2</sub>Zr(CH<sub>3</sub>)<sub>2</sub>)

- 4 -

and boron-containing reagent (e.g., B(R)<sub>3</sub>, where R is preferably a silyl-substituted tetrafluorophenyl group) just prior to polymerization.

5       The Examples which follow set forth certain embodiments of the present invention.

#### EXAMPLE 1

Synthesis of 1-(Dimethyl-t-Butylsilyl)-2,3,5,6-Tetrafluorobenzene (C<sub>6</sub>H<sub>2</sub>F<sub>4</sub>TBS ; TBS = t-butyl, dimethylsilyl)

10       The compound, 1-bromo-2,3,5,6-tetrafluorobenzene, C<sub>6</sub>HBrF<sub>4</sub>, (14.8 g, 64.6 mmol) was dissolved in diethyl ether (200 ml) in a 500 ml flask and was cooled down to -78°C. Butyllithium (40 ml, 1.6 M in hexanes) was then added to the flask dropwise while the solution was being stirred  
15       vigorously. After it had been stirred for one hour, t-butyltrimethylsilyl trifluoromethane sulfonate (17.0 g, 64.6 mmol) was injected via a syringe. The reaction mixture was allowed to slowly warm up to room temperature over a period of eight hours, and the resulting suspension  
20       was filtered. After the solvent was removed from the filtrate at 25°C under reduced pressure, the nonvolatile residue was distilled and a colorless liquid product was collected (45°C/0.8 mm Hg). Yield, 80%, <sup>1</sup>H NMR(CCl<sub>2</sub>D<sub>2</sub>): δ 0.40 (t, 6H), 0.93 (s, 9H), 7.10 (m, 1H); <sup>13</sup>C NMR(CCl<sub>2</sub>D<sub>2</sub>): δ  
25       -3.7(t), 18.1(s), 26.5(s), 108.0(t), 144.8(m), 148.1(t), 151.4(t).

- 5 -

EXAMPLE 2

Synthesis of Bis(Diethyl Ether)Lithium Tetrakis-(4-Dimethyl-t-Butylsilyl-2,3,5,6,-Tetrafluorophenyl) Borate  
 $[(Et_2O)_2Li]^+[B(C_6F_4TBS)_4]^-$

5           The compound synthesized in Example 1, namely,  
1-(dimethyl-t-butylsilyl)-2,3,5,6-tetrafluorobenzene, (5.4  
g, 20.4 mmol) was dissolved in diethyl ether (100 ml) in a  
250 ml flask and was cooled down to -78°C. Butyllithium  
(13 ml, 1.6 M in hexanes) was then added into the flask  
10 dropwise while the solution was being stirred vigorously.  
After it had been stirred for two hours, boron trichloride  
(4.2 ml, 1.0 M in hexanes) was injected via a syringe.  
The reaction mixture was allowed to slowly warm up to room  
temperature over a period of eight hours, and the  
15 resulting suspension was filtered. The volume of the  
solution was reduced to 50 ml and then pentane (130 ml)  
was layered on top of it. The product was collected as  
large colorless crystals after pentane was allowed to  
diffuse into the solution over twenty-four hours, followed  
20 by filtration. Yield, 74%.  $^1H$  NMR( $C_6D_6$ ):  $\delta$  0.20 (s, 24H),  
0.80 (m, 12H), 0.82 (s, 36H), 3.05 (q, 8H);  $^{19}F$  NMR( $C_6D_6$ ):  
 $\delta$  -129.4(b), -133.8(b).

- 6 -

EXAMPLE 3

Synthesis of Triphenylcarbenium Tetrakis(4-Dimethyl-t-Butylsilyl)-2,3,5,6-Tetrafluorophenyl) Borate  
 $[(C_6H_5)_3C]^+[B(C_6F_5)_4]^-$

- 5           The bis(diethyl ether)lithium tetrakis-4-(dimethyl-t-butylsilyl)-2,3,5,6-tetrafluorophenyl) borate synthesized in Example 2 (3.8 g, 3.1 mmol) and triphenylmethyl chloride (0.88 g, 3.1 mmol) were loaded in a 200 ml flask. As pentane (100 ml) was injected into the flask, the
- 10           reaction mixture turned orange immediately. The slurry was stirred for four hours at room temperature and was then filtered. The orange solid was collected and was placed in another 200 ml flask in which  $CH_2Cl_2$  (100 ml) was added. The solution was filtered through to remove
- 15           lithium chloride, and then the volume of the filtrate was reduced to 50 ml. Pentane (100 ml) was added at this point to precipitate an orange solid. The product was washed with pentane (50 ml) again. Yield, 86%,  $^1H$
- 20           NMR( $CCl_2D_2$ ):  $\delta$  0.31 (s, 24H), 0.88 (s, 36H), 7.64 (d, 6H), 7.85 (t, 6H), 8.25 (t, 3H);  $^{19}F$  NMR( $CCl_2D_2$ ):  $\delta$  -133.0(b), -144.5(b);  $^{13}C$  NMR( $CCl_2D_2$ ):  $\delta$  -3.8(s), 17.8(s), 26.4(s), 108.4(s), 131.0(s), 140.2(s), 143.0(s), 144.0(s), 147.4(m), 149.6(m), 211.3(s). Anal. Calcd.: C, 61.55; H, 5.78; N, 0.00. Found: C, 61.83; H, 5.61; N, 0.00.



- 7 -

EXAMPLE 4

Synthesis of Bis(1,2-Dimethylcyclopentadienyl) Methyl Zirconium (I) Tetrakis(4-Dimethyl-t-Butylsilyl-2,3,5,6-Tetrafluorophenyl) Borate  $[\text{Cp}^{\text{H}}_2\text{ZrCH}_3]^+[\text{B}(\text{C}_6\text{F}_4\text{TBS})_4]^-$

5 (Cp<sup>H</sup>=1,2-dimethylcyclopentadienyl)

The triphenylcarbenium tetrakis[(4-dimethyl-t-butylsilyl)-t-butyl-2,3,5,6-tetrafluorophenyl] borate synthesized in Example 3 (390 mg, 0.30 mmol) and bis(1,2-dimethylcyclopentadiene) zirconocene dimethyl (100 mg, 0.32 mmol) were loaded in a 25 ml flask. Toluene (15 ml) was vacuum-transferred into the flask at -78°C. The mixture was then warmed up to room temperature and was stirred for one hour. The resulting pale yellow solution was filtered and the volume of the solution was reduced to 5 ml. Then, pentane (15 ml) was vacuum-transferred into the flask to precipitate the product. The pale yellow product was collected after filtration. Yield, 75%. One thing that is worth mentioning is the outstanding thermal stability of this type of compounds with the anion applied in this patent among all those with other anions. The compound was stable at 100°C for a minimum of two hours and no decomposition was observed by NMR. <sup>1</sup>H NMR(C<sub>6</sub>D<sub>6</sub>): δ 0.21 (s, 24H), 0.34 (s, 3H), 0.83 (s, 36H), 1.37 (s, 6H), 1.61 (s, 6H), 5.00 (b, 2H), 5.69 (b, 2H), 5.97 (t, 2H); <sup>19</sup>F NMR(C<sub>6</sub>D<sub>6</sub>) at 60°C: δ -129.6(b), -131.0(b); <sup>13</sup>C NMR(C<sub>6</sub>D<sub>6</sub>): δ -3.9(s), 12.5(s), 17.7(s), 26.4(s), 45.9(s), 108.1(s), 110.1(m), 111.8(s), 119.8(s), 133.5(b), 147.7(m), 150.9(m). Anal. Calcd.: C, 55.78; H, 6.02; N, 0.00. Found: C, 55.56; H, 6.01; N, 0.00.

- 8 -

EXAMPLE 5Polymerization of ethylene

Bis(1,2-dimethylcyclopentadienyl) methyl zirconium (I) tetrakis[(4-dimethyl-t-butylsilyl)-2,3,5,6-tetrafluorophenyl] borate synthesized in Example 4 (15 mg) was dissolved in toluene (3 ml) in a gas-tight vial in the glove-box. In the meantime, toluene (50 ml) was loaded in a 100 ml flask in the glove-box. The flask was then connected to a vacuum-line and was presaturated with 1.0 atmosphere of ethylene. With ethylene continuing bubbling and the toluene being stirred vigorously, two-thirds of the aforementioned solution of the catalyst was injected into the flask. The reaction could not be stirred in ten seconds due to the production of a large amount of polyethylene. It was quenched by methanol. A yield amount of 0.23 g of polyethylene was obtained. The polymer was collected by filtration and was dried under high vacuum.

EXAMPLE 6Polymerization of propylene

Bis(1,2-dimethylcyclopentadienyl) methyl zirconium (I) tetrakis[(4-dimethyl-t-butylsilyl)-2,3,5,6-tetrafluorophenyl] borate synthesized in Example 4 (15 mg) was loaded in a 100 ml flask in the glove-box. Toluene (50 ml) was vacuum-transferred into the above flask and the solution was exposed to one atmosphere propylene at the room temperature while being stirred vigorously. After being stirred for one-half hour, the reaction was quenched by methanol. A yield of 6.5 g of polypropylene was obtained.

- 9 -

The foregoing Examples, which are presented herein for illustrative purposes only, should not be construed in a limiting sense for that reason. The scope of protection sought is set forth in the claims which follow.

- 10 -

We Claim:

1. An ionic metallocene catalyst for olefin polymerization which comprises: (1) a cyclopentadienyl-type ligand, a Group IVB transition metal, and alkyl, aryl, or hydride substituents, as a cation, and (2) a weakly coordinating anion comprising boron substituted with halogenated aryl substituents containing a bulky organic substituent to improve the solubility and thermal stability of the catalyst as compared to a catalyst containing tetrakis(pentafluorophenyl)boron as the anion.

2. A catalyst as claimed in Claim 1 wherein the aryl substituent in the anion (2) is selected from the group consisting of a phenyl, biphenyl, and naphthyl configuration.

3. A catalyst as claimed in Claim 1 wherein the bulky organic substituent is selected from the group consisting of unsubstituted or substituted C<sub>1</sub> to C<sub>20</sub> alkyl and C<sub>1</sub> to C<sub>20</sub> alkyl-substituted group 14 metalloids.

4. A catalyst as claimed in Claim 1 wherein the bulky organic substituent is an alkyl substituted silyl atom.

5. A catalyst as claimed in Claim 1 wherein the substitution on the halogenated aryl substituents is silyl t-butyl dimethyl.

6. A catalyst as claimed in Claim 5 wherein the substitution is para- on the halogenated aryl substituents.

7. A catalyst as claimed in Claim 1 wherein the aryl substituents in the anion (2) contain four fluoro substituents.

- 11 -

8. A catalyst as claimed in Claim 5 wherein the aryl substituents in the anion (2) contain four fluoro substituents.

5 9. A catalyst as claimed in Claim 6 wherein the aryl substituents in the anion (2) contain four fluoro substituents.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US95/02603

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : B01J 31/02, 31/14

US CL : 502/103, 117, 154

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 502/103, 117, 154

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P --- Y,P	US, A, 5,387,568 (EWEN ET AL.) 07 FEBRUARY 1995, see column 5, lines 20-55; column 4, lines 63-65	1-4,7 ----- 5,6,8,9
X -- Y	US, A, 5,153,157 (HLATKY ET AL.) 06 OCTOBER 1992 see column 4, line 58 to column 6, line 68; column 8, lines 45-68; column 9, lines 3-15; column 13, lines 10-15.	1-4 ----- 5,6,8,9

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*G\* document member of the same patent family

Date of the actual completion of the international search

28 MARCH 1995

Date of mailing of the international search report

05 MAY 1995

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

SHARON GIBSON

Telephone No. (703) 308-0661